

System 100

NEWTON 110 WATSTOP

Epoxy-Cement Waterproofing Mortar & Slurry

Rev 4.3 - 16 April 2019

PRODUCT CODE - 110

INTRODUCTION

Manufactured by Diasen S.R.L. of Sassoferrato, Italy, [Newton 110 WATstop](#) is a three-component, fibre-reinforced cement/epoxy product that, when mixed, produces a workable mortar suitable for surface repair and surface smoothing. With the addition of up to 40% water, a paint/slurry-like consistency can be achieved that is suitable for numerous applications including the damp proofing of walls and slabs and the waterproofing of concrete structures, as well as being a primer for a number of [Newton System 100](#) Liquid Waterproofing products.

APPLICATION



PROPERTIES*

H - Hardness and Durability; E - Elasticity and Flexibility; V - Vapour Resistivity; C - Curing and Drying; W - Working Time; U - UV Stability



PACKAGING



Three-component

COVERAGE



KEY BENEFITS

- Multipurpose solution
- Resistant to up to 9.5 bar of positive and negative pressure
- Excellent adhesion to the most common surfaces used in construction
- Solvent-free
- If applied by trowel it can be applied in just one coat
- If applied by roller or brush it can be applied in one or two coats depending on the coverage

TYPICAL APPLICATIONS

- Surface repair to concrete
- Smoothing of concrete and mortar
- Damp proofing of slabs and walls
- Waterproofing of concrete structures such as lift pits and swimming pools
- Primer for Newton System 100 liquid waterproofing products



* Green is longer or greater, red is less or lower

NEWTON 110 WATSTOP

Epoxy-Cement Waterproofing Coating (Water Barrier)

TECHNICAL DATA

Features	Result					Units
Form	Semi-dense paste					
Colour	Black					
Density/Specific Gravity	1.34					
Packaging – Bucket	5 & 10					kg
Shelf life	12					Months
Pot life at 20°C and 40% relative humidity	2					Hours
Application rate – Mortar (As mixed)	Depends on surface irregularities					
Application rate – Primer (Water added up to 40% of volume)	0.3					kg/m²
Application rate – Gas, vapour control layer & Floor DPM (Water added as above)	0.6					kg/m²
Application rate – Wall DPM (Water added as above)	1.0					kg/m²
Application rate – Waterproofing (Water added as above)	2.0					kg/m²
Application method	Trowel as mortar, roller or brush as liquid					
Application temperature	+5 to +35					°C
Service temperature	-30 to +60					°C
Odour	Strong epoxy					
VOC content	None					
pH	10.85					
Curing	5°C	10°C	15°C	20°C	25°C	Units
Ready for next coat	10	8	5	5	5	Hours
To not be adulterated by rain	48	36	24	24	24	Hours
Ready for temporary foot traffic / protection boards	48	36	24	24	24	Hours
Ready for flood / hosepipe test	7	3	2	2	2	Days
Fully cured	7	3	2	2	2	Days
Cured Performance	Result		Units		Test Method	
Colour	Black					
Membrane thickness – Primer	0.22		mm			
Membrane thickness – Gas, vapour control layer & Floor DPM	0.44		mm			
Membrane thickness – Wall DPM	0.75		mm			
Membrane thickness – Waterproofing	1.5		mm			
Adhesion to concrete	2.5		N/mm²		UNI EN ISO 4624	
Tensile strength	Very low				Not tested	
Elongation	Very low				Not tested	
Loading capability	Very high				Not tested	
Hardness	Very high				Not tested	
Impact resistance	Very high				Not tested	
Puncture resistance	Very high				Not tested	
Water vapour diffusion resistance – Sd value	13.3		m		Calculation from μ value	
Water vapour diffusion resistance – 2mm film - μ value	13361		μ		UNI ISO 7783	
Water vapour diffusion resistance	66.8		MNs/g		Calculation from μ value	
Water tightness – Positive side	9.5		atm		UNI EN ISO 12390-8	
Water tightness – Negative side	9.5		bar		See note 1 below	
Reaction to fire classification	Euroclass E				Not tested	
Solvent resistance	None					
Organic acid resistance	None					
UV Resistance – Stable	10.0		Years		UNI EN ISO 11507	
Freeze / thaw resistance – 50 cycles	Unchanged				UNI EN 202	

¹ Testing was conducted by an independent laboratory. Test report is available on request.

NEWTON 110 WATSTOP

Epoxy-Cement Waterproofing Coating (Water Barrier)

SUITABLE SUBSTRATES

- Concrete
- Structural masonry
- Ceramic
- Steel
- Screed
- Ferrous metal
- PVC

SUITABLE SURFACES

Waterproofing of:

- Walls - Positive pressure and negative pressure
- Slab/raft - Negative pressure
- Soffit - Negative pressure
- Deck - Positive pressure

METHOD OF APPLICATION

Mortar

- Putty knife
- Trowel

Liquid (after up to 40% water is added)

- Brush
- Roller

SPECIFICATION

Newton Waterproofing Systems are in partnership with RIBA NBS who publish details of our products and systems within their specification clause library to allow Architects ease of specification through their NBS Plus interface. NBS clauses can be accessed via the technical resources area of the web site where a live NBS Feed is available at [NBS Plus Live Feed](#)

Our website has drawings available for download in [Technical Drawings](#). A selection are also available via [FastrackCAD](#), as well as a range of BIM objects on the [NBS National BIM Library](#)

TRAINING AND COMPETENCY OF THE USER

The diagnosis of damp and the specification of correct use of Newton 110 WATstop will, in many cases, require the intervention of a specialist in the field of damp remediation. When used as part of a waterproofing specification, Newton 110 WATstop should be installed by those with experience of structural waterproofing.

It is recommended that Newton 110 WATstop and its ancillary products be installed by contractors trained by Newton Waterproofing Systems in the correct use and specification of the product.

LIFE EXPECTANCY

When specified, installed and protected in accordance with the Data Sheet, and fully and permanently isolated from UV light and physical damage or wearing, and only to those substrates confirmed within, Newton 110 WATstop has a service life that can be equal to the design life of the structure.

Newton 110 WATstop is guaranteed to resist weathering for up to 10-years but it is not recommended to leave the product exposed.

COATING & PROTECTION

Newton 110 WATstop should be covered after application:

Protection methods include:

- Plaster or render
- Ceramic tiling
- Newton System 100 Liquid Waterproofing Membranes
- Coloured sands or grit 100% broadcasted to the still tacky final coat to provide an abrasion and slip resistant finish.
- Water-based emulsion paints

Coatings, paints and finishes can be applied up to 72 hours after the final coat of Newton 110 WATstop has been applied.

LIMITATIONS

- Do not apply prior to heavy rain - please see information within the curing table on page 2
- Do not apply at temperatures lower than +5°C or higher than +35°C
- Always use the correct preparation and priming of the support substrate as directed within this data sheet.

PACKAGING

- 5 kg tub - Purchase Code 110-5
- 10 kg tub - Purchase Code 110

YIELD AS MORTAR

7.5 litres per 10 kg tub.

APPLICATION RATE

Newton 110 WATstop is applied in one, or two coats depending on the application:

PRIMER

- Number of coats = 1
- Thickness of coat = 0.22 mm
- Total thickness = 0.22 mm
- Coverage per coat = 0.3 kg/m²
- Total coverage = 0.3 kg/m²
- Coverage per 10kg container = 33 m²

NEWTON 110 WATSTOP

Epoxy-Cement Waterproofing Coating (Water Barrier)

GAS, VAPOUR CONTROL LAYER & FLOOR DPM

- Number of coats = 2
- Thickness per coat = 0.22 mm
- Total thickness = 0.44 mm
- Coverage per coat = 0.30 kg/m²
- Coverage rate = 0.60 kg/m²
- Total coverage per 10 litre container = 16 m²

WALL DPM

- Number of coats = 2
- Thickness per coat = 0.38 mm
- Total thickness = 0.75 mm
- Coverage per coat = 0.50 kg/m²
- Coverage rate = 1.0 kg/m²
- Total coverage per 10 litre container = 10 m²

WATERPOOFING

- Number of coats = 2
- Thickness per coat = 0.75 mm
- Total thickness = 1.50 mm
- Coverage per coat = 1.00 kg/m²
- Coverage rate = 2.00 kg/m²
- Total coverage per 10 litre container = 5 m²

SURFACE PREPARATION

- The surface must be clean, and free from dust, laitance, or other forms of contamination. This may require wall surface preparation such as grit blasting or scabbling
- Fill holes and any non-structural cracks with the product in mortar consistency
- Remove snots
- Newly laid concrete to slabs and rafts should have a uniform, dense and smooth surface with float marks of no more than 3mm. A U5 power floated finish with no float marks is also suitable but not required as the surface will be ground to remove laitance. U1 (Abrupt irregularities permitted) or U2 (Tamp marks of up to 10mm) finishes should be avoided
- In all cases, concrete floors should be ground with floor grinding products to remove laitance. Vacuum clean after grinding. All structural cracks should be repaired and filled

JOINTS & CHANGES OF DIRECTION

- Reinforce static joints with [Newton 912-RT](#)
- With shrinkage joints, stop either side of the joint and use the movement joint detail for the liquid membrane to be used above the 110 WATstop
- With movement joints, lap into the joint and then use our standard [Newton 106 FlexProof](#) movement joint detail. Please speak to our Technical Department if you require assistance on the correct specification to joints

MIXING

MORTAR

- Open the epoxy paste (part A) and pour it completely into the larger bucket. Scrape out all remnants of the epoxy
- Open the cement (part C) and pour it slowly into the larger bucket whilst slowly mixing. Again, scrape out all remnants
- Open the catalyst (part B) and pour completely into the mixing bucket. Scrape out all remnants,
- Mix for 2 minutes at slow speed using a suitable mixer and paddle (please see below) until a homogenous paste, with no lumps, is achieved
- Do not close the lid - The mixing of Newton 110 WATstop produces an exothermic reaction
- Use immediately after mixing
- Add water to the mortar mix as required

SLURRY

- Carefully add water at up to 40% of weight to achieve a low viscosity slurry/paint mixture
- Adding too much water will inhibit the effectiveness of the product
- Mix for a minimum of 2 minutes and use without delay

Newton Waterproofing supply the full range of [Collomix Mixing Equipment](#) that includes Hand-Mixers, Stirrers, Mixing Stands, Buckets, Transport Carts and the Mixer Clean mixing bucket. Newton 110 WATstop can be mixed with the DLX and WK stirrers, matched to the Xo 1 or Xo 4 Hand Mixers which are suitable for quantities of up to 65 litres. For larger quantities the MKD dual action stirrer is matched to the Xo 55 duo Hand-Mixer.

APPLICATION - MORTAR

The mortar can be applied by trowel or putty knife in the same way as a standard mortar.

APPLICATION - SLURRY

The mixed slurry can be applied by brush or roller.

Apply as explained within the APPLICATION RATE section, which begins on page 3.

With two coat applications, the second coat should be applied when the first coat is fully dry to touch and up to 72 hours after the first coat has been applied.

APPLICATION - WALL DPM

Extend the treatment 250mm above the highest sign of rising damp.

CURING

Curing is by exothermic reaction and so the product does not need to be traditionally cured.

NEWTON 110 WATSTOP

Epoxy-Cement Waterproofing Coating (Water Barrier)

COLOUR

Black.

COATINGS AND FINISHES

Coatings, paints and finishes can be applied up to 72 hours after the final coat of Newton 110 WATstop has been applied.

STORAGE

Store in dry conditions at temperatures between +5°C and +35°C with containers fully sealed. Do not expose to freezing conditions.

If these conditions are maintained and the product packaging is unopened, a shelf life of up to 12 months can be expected.

CLEANING

Thoroughly clean all tools and equipment with water immediately after use.

POT LIFE & FURTHER USE

Newton 110 WATstop has an approximate pot life of 120 minutes at +20°C.

Product must be used within this period.

ANCILLARY PRODUCTS

- Newton 912-RT - Purchase Code 912-RT.
Reinforcement Tape for reinforcing changes in direction and static joints

HEALTH & SAFETY

Use appropriate PPE for the environment the system is installed within. Use products only as stated within this Data Sheet and the MSDS.

Any specification/advice provided is only valid if used with products supplied by John Newton and Company Ltd (trading as Newton Waterproofing Systems). Newton Waterproofing Systems reserve the right to update product literature at any time. Please always refer to our [website](#) for the latest versions.