

OVERVIEW

PU ADDAFLAKE is a two pack fast curing polyurethane coloured base coat designed to hold a blend of coloured quartz, coloured flakes or as a pigmented UV stable top coat with excellent scratch resistance.

PREPARATION OF SURFACE

The surface to be treated should be free of laitance, oil, grease and loose friable particles which could affect adhesion. Vacuum assisted shot blasting or grinding of the surface is recommended. The substrate must have a maximum of 4% moisture content and be protected against any moisture ingress from underneath.

MIXING & APPLICATION

PU ADDAFLAKE is supplied in units ready to use, comprising of Part 'A' (Resin) and Part 'B' (Hardener). First stir thoroughly contents in container 'A' to a homogenous consistency, then scrap contents of 'B' into container 'A' and mix thoroughly for several minutes using a low speed electric drill. Use protective gloves and goggles. Failure to mix thoroughly will result in poor or non cured material. Keep all containers at room temperature 24 hours before use.

The temperature of the substrate must be 3 degrees above the dew point temperature of the room. See Addagrip Dew Point table for assistance. PU ADDAFLAKE should not be applied at temperatures below 10°C nor above 30°C. Relative humidity should not exceed 80%.

Apply the mixed PU ADDAFLAKE immediately by serrated trowel, floor finish scraper or squeegee onto the prepared surface. Particular attention should be given to areas around obstructions and protrusions making sure that all surfaces are covered.

HEALTH & SAFETY

Before using this product, please ensure you have been supplied and have read carefully the following:-

1. The hazard label (complying with CLP – European Regulation (EC) No. 1272/2008 on Classification, Labelling and Packaging of substances and mixtures) applied to the container.

2. Safety Data Sheet

Avoid prolonged contact with eyes and skin. For detailed information refer to relevant safety data sheet.

PACKAGING & STORAGE

Packaged in 2.5kg or 5kg units. Store containers in a clean dry area protected from direct sunlight and extreme heat and cold. Unopened containers can be stored for 3 months. Use oldest material first.

CLEANING OF EQUIPMENT & SKIN

Tools, brushes etc... should be cleaned immediately after use in Addagrip Solvent Mixture. For cleaning of hands/skin, use a deep cleaning soap with water. Please note if a rash appears seek medical attention.

DISPOSAL CONSIDERTIONS

Normally the Part A resin will be mixed in its own container with Part B. When this is done correctly the resultant material in the container is inert and the label must be defaced. The container and remnant may be disposed of as normal industrial waste. Any uncured material must be disposed as hazardous waste. Please consider the regional or national regulations regarding disposal.

TECHNICAL DATA

Product	Fast curing base/top coat
Density	1.4-1.5g/cm ³
Colour	White or Black
Application Temperature	+10°C to 30°C
Surface Temperature	Must be 3°C above the dew point temperature.
Pot life at 20°C	15 minutes (Useable life maximum 20 minutes)
Initial cure at 20°C	Initially 2-3 hours, full chemical cure 7 days
Material Consumption/Coverage	Approx. 0.45kg/m ²
Slip potential	Low when dry, high when wet. (Slider 96)
Packaging	Supplied in 2.5kg and 5kg units (3.17:1 mix ratio by weight)
Storage	3 months in original unopened containers.

CE MARKING

CE	
<i>Addagrip Terraco Ltd, Bell Lane Industrial Estate, Uckfield, East Sussex, TN221QL</i>	
13	
EN 13813 SR-B2.0-AR0.5-IR>9.8	
<i>Synthetic resin screed material for use internally in buildings</i>	
Reaction to fire:	B _{fl} -s1
Release of corrosive substances:	SR
Wear resistance:	AR0.5 ¹
Bond strength:	B2.0 ²
Impact resistance:	IR>9.8
Compressive strength:	NPD ³
Flexural strength:	NPD ³
Surface hardness:	NPD ³
Resistance to rolling wheel with floor covering:	NPD ³
Shrinkage and swelling:	NPD ³
Consistency:	NPD ³
pH value:	NPD ³

- 1) Determined according to BCA method.
- 2) Coating did not disbond from concrete.
- 3) NPD: Characteristic value not specified.

For technical enquiries please contact your nearest representative:

UK:
ADDAGRIP
Tel: +44 (0)1825 761 333
E-mail: sales@addagrip.co.uk
Web: www.addagrip.co.uk / www.terraco.com